

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
26 September 2002 (26.09.2002)

PCT

(10) International Publication Number
WO 02/074912 A2

- (51) International Patent Classification⁷: C12N
Stephen, B.; 59 Woodland Road, Auburndale, MA 02114 (US). FREED, Lisa, E.; 34 Palfrey Road, Belmont, MA 02478 (US). LANGER, Robert; 98 Montvale Road, Newton, MA 02459 (US).
- (21) International Application Number: PCT/US02/07805
- (22) International Filing Date: 14 March 2002 (14.03.2002)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
09/809,456 15 March 2001 (15.03.2001) US
- (74) Agent: JARRELL, Brenda, H.; Choate, Hall & Stewart, Exchange Place, 53 State Street, Boston, MA 02109 (US).
- (81) Designated States (*national*): CA, JP.
- (84) Designated States (*regional*): European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR).
- (71) Applicant: MASSACHUSETTS INSTITUTE OF TECHNOLOGY [US/US]; 77 Massachusetts Avenue, Cambridge, MA 02138 (US).
Published:
— without international search report and to be republished upon receipt of that report
- (72) Inventors: MADRY, Henning; Volhardstrasse 7, 66424 Homburg (DE). VUNJAK-NOVAKOVIC, Gordana; 305 Fitzmaurice Circle, Belmont, MA 02478 (US). TRIPPEL, —
For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: TISSUE ENGINEERING ENHANCED BY THE TRANSFER OF A GROWTH FACTOR GENE

(57) Abstract: Tissue engineered constructs including a matrix and cells transfected with a gene for a growth factor. The constructs may be implanted into a tissue site, where the growth factor gene enhances a metabolic function furthering integration of the construct in the tissue site. If the matrix is biodegradable, the metabolic result may include resorption of the matrix and replacement with tissue synthesized at least in part by the transfected cells.

WO 02/074912 A2

TISSUE ENGINEERING ENHANCED BY THE TRANSFER OF A GROWTH FACTOR GENE

This invention was partially made with Government support under grants

- 5 NAG 9-836 and NCC 8-174 from the National Aeronautical and Space
Administration and AR 31068 and AR 45749 from the National Institutes of Health.
The United States Government has certain rights in this invention. This invention was
also partially made with assistance from Leopoldina Fellowship Grant BMBF-LPD
9801-10.

10

Field of the Invention

This invention pertains to the use of genetically enhanced cells for tissue
engineering and, more particularly, to the use of cells transfected with genes for
growth factors.

Background of the Invention

15

- Physiological tissues and organs have adopted a variety of mechanisms for
healing wounds and defects. For example, a cut in the skin may be healed by the
formation of fibrous tissue, or scar, that connects the edges of the wound and protects
interior tissues from the environment. Scar does not have the same mechanical or
biological properties as undamaged skin. This healing mechanism, called repair, does
20 not replace the structure or function of the original, undamaged tissue.

- In contrast, organs such as liver have the ability to regenerate, replacing the
wounded tissue with new, fully functional tissue having the same biological and
mechanical properties as the original. Many tissues that typically heal by repair also
have the ability to heal by regeneration. For example, small wounds such as paper
25 cuts in the skin typically heal by regeneration, while larger wounds such as burns heal

by formation of scar tissue. Furthermore, there are some tissues that do not properly heal at all on their own. To remedy defects and injuries in such tissue, physicians frequently attempt to artificially promote, repair or regeneration in such tissues.

In one example, articular cartilage lesions do not heal properly if left untreated, yet effective treatment methods remain an unsolved problem (Buckwalter, (1998) "Articular cartilage repair and transplantation." Arthritis. Rheum. 41: 1331-1342). Tissue engineering (Langer, *et al.* (1993) "Tissue Engineering." Science 260: 920-6) and gene therapy (Mulligan, (1993) "The basic science of gene therapy." Science 260: 926-932) are two novel approaches to regenerate articular cartilage (see Evans, *et al.* (1999), "Genetically augmented tissue engineering of the musculoskeletal system" Clin. Orthop. 367Suppl.:S410-418). Three-dimensional, functional cartilaginous tissue can be generated in bioreactors using isolated chondrocytes cultured on biodegradable scaffolds (Freed, (1997) "Tissue engineering of cartilage in space." Proc. Natl. Acad. Sci. U S A 94: 13885-90; Vunjak-Novakovic, *et al.*, (1999) "Bioreactor cultivation conditions modulate the composition and mechanical properties of tissue engineered cartilage." J Orthop. Res. 17: 130-138). The functional properties of the engineered constructs develop over the time of cultivation and come into the range of values measured for native articular cartilage only after several months of culture (Freed, 1997). Moreover, adult articular chondrocytes are problematic as a cell source for a clinical scenario of therapeutic tissue engineering due to their very low mitotic activity. However, isolated articular chondrocytes can be genetically modified (Baragi, *et al.* (1995) "Transplantation of transduced chondrocytes protects articular cartilage from interleukin 1-induced extracellular matrix degradation." J. Clin. Invest. 96: 2454-60; Kang *et al.*, (1997) "Ex vivo gene transfer to chondrocytes in full-thickness articular cartilage defects: A

feasibility study." Osteoarthritis Cartilage 5: 139-43; Doherty *et al.*, (1998)

"Resurfacing of articular cartilage explants with genetically-modified human chondrocytes in vitro." Osteoarthritis Cartilage 6: 153-9; Madry, *et al.* (2000)

"Efficient lipid-mediated gene transfer to articular chondrocytes." Gene Ther. 7: 286-91) to express potentially beneficial genes (Doherty, 1998; Madry, 2000; Smith, *et al.* (2000) "Genetic enhancement of matrix synthesis by articular chondrocytes." J. Rheumatol. 43: 1156-64). Insulin-like growth factor-I (IGF-I), a 7.6 kDa polypeptide growth factor, is a candidate gene to improve tissue engineering of cartilage, as it stimulates chondrocyte mitotic activity, increases proteoglycan and type-II collagen synthesis *in vitro* (Trippel, *et al.* (1997) "Growth factors as therapeutic agents." Instr. Course. Lect. 46: 473-6) and enhances articular cartilage repair *in vivo* (Nixon, *et al.* (1999) "Enhanced repair of extensive articular defects by insulin-like growth factor-I-laden fibrin composites." J. Orthop. Res. 17: 475-87). The application of chondrocytes that were genetically modified *ex vivo* to articular cartilage defects (Kang, 1997) is complicated due to technical challenges, such as the problem of cell loss after transplantation (O'Driscoll, *et al.* (1998), "The healing and regeneration of articular cartilage." J. Bone Joint Surg. Am. 80: 1795-12). Moreover, direct gene transfer into cartilage is difficult due to the dense matrix in which the chondrocytes are embedded (Ikeda, *et al.* (1998). "Adenovirus mediated gene delivery to the joints of guinea pigs." J. Rheumatol. 25: 1666-73).

Gene transfer has been successfully applied to the tissue engineering of bioartificial muscle expressing a therapeutic protein (Powell, *et al.* (1999) "Tissue-engineered human bioartificial muscles expressing a foreign recombinant protein for gene therapy." Hum. Gene Ther. 10: 565-77) or to achieve the sustained release of plasmid DNA when associated with a biodegradable carrier *in vivo* (Bonadio, *et al.*

(1999) "Localized, direct plasmid gene delivery *in vivo*: prolonged therapy results in reproducible tissue regeneration." Nat. Med. 5: 753-9). Recent studies have demonstrated that isolated articular chondrocytes can be genetically modified (Baragi, 1995; Kang, 1997; Doherty, 1998; Madry, 2000) to express potentially beneficial
5 genes (Baragi, 1995; Smith, 2000). Insulin-like growth factor-I (IGF-I), a 7.6 kDa polypeptide growth factor, stimulates chondrocyte mitotic activity, increases proteoglycan and type-II collagen synthesis *in vitro* (Trippel, 1997) and enhances articular cartilage repair *in vivo* (Nixon, 1999).

One approach to tissue engineering is to promote regeneration of lost or
10 damaged tissue by providing materials that facilitate regenerative processes. For example, cells may be implanted into a wound site and allowed to generate extracellular matrix and other molecules that ordinarily form part of the normal tissue. Cells may also be taken from a patient or other source and utilized to synthesize tissue *in vitro*, following which the naturally synthesized tissue is transferred to the wound
15 site.

Alternatively, a wound site may be implanted with a synthetic extracellular matrix that initially promotes migration of cells from the edges of a wound and later promotes normal metabolic and synthetic activity in the cells, enabling them to produce new tissue that will eventually replace the implanted matrix. Alternatively,
20 these matrices may be coated with growth factors or other regulators designed to up-regulate certain metabolic activities in cells. They may also be coated with genetic material, which is then taken up into the cells where they control the production of desired proteins. *In vitro* cell cultures are also frequently transfected with DNA for specific growth factors or regulators. The DNA may be transferred directly into the
25 cells or placed in the cell culture, where the cells uptake the genetic material through

their membranes. However, the efficiency of cellular uptake of DNA varies, and some cells, such as chondrocytes, have not been demonstrated to uptake DNA immobilized on a cellular scaffold. Thus, it is desirable to employ more reliable transfection techniques for cells that are seeded in matrices for tissue engineered implants. It is hypothesized that the utilization of genetically engineered cells will improve the functionality of engineered tissue, while the incorporation of genetically engineered cells will improve cell delivery to the implantation site.

Summary of the Invention

In one aspect, the invention is a method of assembling a tissue engineered construct. The method comprises transfecting a plurality of mammalian cells with a gene for a growth factor. The method may further comprise culturing the cells until they synthesize a desired amount of extracellular matrix or seeding the cells onto a biocompatible matrix. The matrix may comprise a synthetic or a nonsynthetic material. For example, the matrix may comprise poly(glycolic acid), collagen-glycosaminoglycan, collagen, poly(lactic acid), poly(lactic-co-glycolic acid, poly(anhydride), poly(hydroxy acid), poly(orthoester), poly(propylfumerate), polysaccharide, polypyrrole, polyaniline, polythiophene, polystyrene, polyester, polyurethane, polyurea, poly(ethylene vinyl acetate), polypropylene, polymethacrylate, polyethylene, poly(ethylene oxide), poly(carbonate), or any combination thereof. The cells may be human cells, for example, chondrocytes, hepatocytes, Islet cells, nerve cells, muscle cells, bone-forming cells, fibroblasts, endothelial cells, stem cells, connective tissue stem cells, mesodermal stem cells and epithelial cells. A cell attachment facilitator may be attached to the matrix. The facilitator may comprise an integrin, cell adhesion sequence, basement membrane component, agar, or collagen. In addition, a cell metabolism regulator may be added

to the matrix. The growth factor may be a protein, for example, TGF- β , acidic fibroblast growth factor, basic fibroblast growth factor, epidermal growth factor, IGF-I or II, vascular endothelial-derived growth factor, bone morphogenetic proteins, platelet-derived growth factor, heparin-binding growth factor, hematopoietic growth factor, or peptide growth factor. The transfection may be accomplished with or without a viral vector. For example, transfection may be accomplished with a lipid-based delivery system.

In another aspect, the invention is a tissue engineered construct comprising a mammalian cell transfected with a gene for a growth factor and a biocompatible synthetic matrix. In another aspect, the invention is a method for facilitating regeneration of cartilage. The method comprising transfecting a chondrocyte with a gene for a growth factor, seeding the chondrocyte onto a biocompatible synthetic matrix, and implanting the cell-seeded matrix into an *in vivo* site. The synthetic matrix may comprise poly (glycolic acid), the growth factor may be insulin-like growth factor I, and transfection may be accomplished without a viral vector, for example, with a lipid-based delivery system.

In another aspect, the invention is a transfection vector for a mammalian cell, including a gene for a growth factor. The cell may be a chondrocyte, a hepatocyte, Islet cell, nerve cell, muscle cell, bone-forming cell, fibroblast, endothelial cell, stem cell, connective tissue stem cell, mesodermal stem cell, or epithelial cell. The growth factor may be a protein, for example, TGF- β , TGF- α , acidic fibroblast growth factor, basic fibroblast growth factor, epidermal growth factor, IGF-I and II, vascular endothelial-derived growth factor, bone morphogenetic proteins, hepatocyte, platelet-derived growth factor, heparin binding growth factor, hematopoietic growth factor, or peptide growth factor. The gene may include human IGF-I expression vector

pCMVhIGF-I. The gene may comprise an active fragment that is 50%, 75% or 90% homologous to the complete gene for IGF(I). The transfected gene may code for a portion of normal IGF-I that is 50%, 75% or 90% homologous to complete IGF-I.

In another aspect, the invention is a plurality of transfected cells comprising chondrocytes. The chondrocytes are transfected with a gene for a protein, the protein may be a growth factor, for example, insulin-like growth factor I. The cells may be transfected with a vector pCMVhIGF-I.

Brief Description of the Drawing

The invention is described with reference to the several figures of the drawing, in which,

Figure 1 is a schematic showing the transfection and seeding method used in the invention;

Figure 2A is a graph depicting the wet weight of engineered constructs seeded with chondrocytes transfected with ((o) lacZ expression plasmid vector pCMVSPORT β GAL, (•) the human IGF-I expression plasmid vector pCMVhIGF-I, or (□) non-transfected chondrocytes at 10, 21, and 28 days post-transfection (n = 10);

Figure 2B is light micrographs of cross-sections of experimental and control constructs that were stained *in toto* with x-gal 28 days post-transfection (top: IGF-I group, middle: non-transfected group, bottom: lacZ-transfected group);

Figure 2C includes light micrographs of experimental and control constructs that were stained *in toto* with safranin O 28 days post-transfection (top: IGF-I group, middle: non-transfected group, bottom: lacZ-transfected group);

Figures 3A, B, C, D, E, F, G, H, I, K, L, and M are horizontal sections of experimental and control constructs seeded with articular chondrocytes 28 days post-

transfection with (A, D, G, K) *lacZ* expression vector pCMVSPORT β Gal, (B, E, H, L) the human IGF-I expression vector pCMVhIGF-I, or (C, F, I, M) non-transfected chondrocytes (stains: A-C: Safranin O, D-F: a monoclonal anti-type I collagen antibody, G-I: a polyclonal anti-type II collagen antibody, K-M: monoclonal
5 aggrecan antibody).

Detailed Description

The file of this patent contains at least one drawing executed in color. Copies of this patent with color drawings will be provided by the Office upon request and payment of the necessary fee.

10 The invention employs a tissue engineered construct incorporating cells that have been transfected with a particular growth factor or regulator. The invention also includes a tissue engineering method wherein transfected cells are seeded on a synthetic, biodegradable matrix and implanted into a tissue site.

The invention can be practiced with a wide variety of cells. Matrices
15 incorporating cells from a variety of tissues have been exploited in tissue engineering applications and can be employed for use with the present invention. For example, chondrocytes have been seeded on type-II collagen matrices, poly(lactic acid), poly(glycolic acid), PLA-PGA, or other matrices. Hepatocytes, islet cells, nerve cells, muscle cells, other organ cells, bone or cartilage forming cells, other connective tissue
20 cells such as epithelial and endothelial cells, and stem cells such as connective tissue stem cells and mesodermal stem cells may also be seeded on matrices for use with the invention. One skilled in the art will recognize that tissue engineering techniques may be applied to a myriad of hard and soft tissues including metabolic tissue (*e.g.*, liver or pancreas), connective tissue (*e.g.*, skin, bone), and nerve.

25 For therapeutic applications, it is preferable to practice the invention with

mammalian cells, and more preferably human cells. Preferably, the cells are HLA matched with the patient, and, most preferably, the patient's own cells are harvested, transfected, and used to seed the matrices of the invention. The cells may be obtained from cell line culture, biopsy, tissue banks, or other sources known to those skilled in the art.

These cells may be seeded on a wide variety of biocompatible matrices. Preferably, the matrix is also biodegradable. Suitable biodegradable matrices are well known in the art and include collagen-GAG, collagen, fibrin, PLA, PGA, and PLA-PGA co-polymers. Additional biodegradable materials include poly(anhydrides), poly(hydroxy acids), poly(ortho esters), poly(propylfumerates), poly(caprolactones), polyamides, polyamino acids, polyacetals, biodegradable polycyanoacrylates, biodegradable polyurethanes and polysaccharides. Non-biodegradable polymers may also be used as well. For example, polypyrrole, polyanilines, polythiophene, and derivatives thereof are useful electrically conductive polymers that can provide additional stimulation to seeded cells beyond the regulators synthesized by the transfected DNA. Other non-biodegradable, yet biocompatible polymers include polystyrene, polyesters, non-biodegradable polyurethanes, polyureas, poly(ethylene vinyl acetate), polypropylene, polymethacrylate, polyethylene, polycarbonates, and poly(ethylene oxide). Those skilled in the art will recognize that this is an exemplary, not a comprehensive, list of polymers appropriate for tissue engineering applications.

It is preferred that the matrix be formed with a microstructure similar to that of the extracellular matrix that is being replaced. Mechanical forces imposed on the matrix by the surrounding tissue will influence the cells on the artificial matrix and promote the regeneration of extracellular matrix with the proper microstructure. The cross-link density of the matrix may also be regulated to control both the mechanical

properties of the matrix and the degradation rate (for degradable scaffolds). The shape and size of the final implant should be adapted for the wound site and tissue type.

PLA, PGA and PLA/PGA copolymers are particularly useful for forming the biodegradable matrices. PLA polymers are usually prepared from the cyclic esters of lactic acids. Both L(+) and D(-) forms of lactic acid can be used to prepare the PLA polymers, as well as the optically inactive DL-lactic acid mixture of D(-) and L(+) lactic acids. PGA is the homopolymer of glycolic acid (hydroxyacetic acid). In the conversion of glycolic acid to poly(glycolic acid), glycolic acid is initially reacted with itself to form the cyclic ester glycolide, which in the presence of heat and a catalyst is converted to a high molecular weight linear-chain polymer. The erosion of the polyester matrix is related to the molecular weights. The higher molecular weights, weight average molecular weights of 90,000 or higher, result in polymer matrices which retain their structural integrity for longer periods of time; while lower molecular weights, weight average molecular weights of 30,000 or less, result in both slower release and shorter matrix lives. For example, poly(lactide-co-glycolide) (50:50) degrades in about six weeks following implantation.

Any biocompatible polymer is suitable so long as it may be formed into a matrix having the necessary porosity for cell viability. The porosity should be such that nutrients can migrate to the cells and waste products can diffuse away from the cells. The pores should also be large enough for the residence of the cells themselves. The pore size is typically in the range of 50-300 μm and, as noted above, it may be varied within this range to control cell behavior and matrix properties (see U.S. Patent No. 6,123,727 to Vacanti, *et al.*, the entire contents of which are incorporated herein by reference). Furthermore, within the range of pore size that promotes proper cell metabolism, the size and arrangement of the pores may be controlled to promote a

specific timetable and amount of vascular ingrowth from the surrounding tissue as well as migration of native cells and the diffusion of nutrients.

The matrix material may be coated with materials that promote specific adhesion and metabolic behavior of both transfected cells and native cells, using techniques well known in the art. For example, integrins or other cell adhesion molecules may be attached to the matrix. Cell attachment may also be enhanced by coating the matrix with materials such as basement membrane components (*e.g.*, laminin, fibronectin), agar, agarose, collagens types I, II, III, or IV, glycosaminoglycans, polyvinyl alcohol, and other hydrophilic materials and mixtures thereof. Alternatively, amino acids such as lysine or poly(lysine) may be coated onto the matrix. Regulators or growth factors such as TGF- β may also be attached to the matrix to promote specific metabolic activity. Other bioactive molecules that may be attached to the matrix or incorporated into the matrix during cell seeding include growth factors such as fibroblast growth factor, epidermal growth factor, or various morphogenic factors known to those skilled in the art. Such bioactive molecules are well known in the art and are commercially available or described in both the tissue engineering and endocrinology literature. An effective dosage of a given growth factor or regulator for a given cell may be determined experimentally *in vitro* by determining a dosage that increases cell proliferation, metabolism, or survival as compared with untreated controls. In addition, an anti-inflammatory agent may be used to decrease inflammation in the implanted matrix, decreasing the growth of scar-like tissue into the matrix.

The cell may be transfected with a nucleic acid encoding specific regulators and cytokines. Other molecules, genes, or nucleic acids that influence cell growth, matrix production, or other cellular functions such as cell cycle may also be used.

Nucleic acids may be DNA, RNA, or other nucleotide polymers. Such polymers may include natural nucleosides, nucleoside analogs, chemically modified bases, biologically modified bases, intercalated bases, modified sugars, or modified phosphate groups. The growth factors encoded may include those described above and others that are well known to those skilled in the art. For example, fibroblasts may be transfected with TGF- β . As noted above, chondrocyte metabolism is increased by IGF-I, and muscle cells have been successfully transfected with genes for therapeutic proteins (Powell, 1999). Other exemplary growth factors include epidermal growth factor, bone morphogenetic protein, vascular endothelial-derived growth factor, hepatocyte growth factor, platelet-derived growth factor, TGF α , IGF-II, hematopoietic growth factors, heparin binding growth factor, peptide growth factors, and basic and acidic fibroblast growth factors. In some embodiments it may be desirable to incorporate genes for factors such as nerve growth factor (NGF) or muscle morphogenic factor (MMP). The particular growth factor employed should be appropriate to the desired cell activity. The regulatory effects of a large family of growth factors are well known to those skilled in the art.

Vectors containing the transfected gene may be any of those known in the art. The gene may be transfected into a cell using a linear piece of nucleic acid, a circular plasmid, a ss-nucleic acid, a ds-nucleic acid, a virus, a YAC, etc. The complete gene for the growth factor may be transfected, or active fragments of the gene that are 50, 75, or 90% homologous to the complete gene may be used. The transfected gene may code for the entire growth factor protein, for a peptide including a portion of the protein, or for portions of the protein that are 50, 75, or 90% homologous to the growth factor.

A variety of gene transfection techniques are known in the art. For example,

viral vectors such as adenovirus are commonly used to insert DNA into a variety of cells. Other transfection methods include electroporation, Ca-phosphate methods, and lipid based methods. A wide variety of techniques are well known in the art (Sambrook *et al.*, Molecular Cloning: A Laboratory Manual, 2nd Ed., 1989; Miller and Calos, eds., Gene Transfer Vectors for Mammalian Cells, 1987; Ausubel *et al.*, eds., Current Protocols in Molecular Biology, 1987; each of which is incorporated herein by reference). Both stable transfection and transient expression techniques may be employed, depending on how long the growth factor should be expressed. For example, a growth factor promoting a wound healing response need only be produced for a few days, while it may be desirable to express a gene for a factor regulating metabolic activity for a longer period of time.

The gene encoding the growth factor to be expressed may be operably linked to other elements regulating expression of the gene, including, but not limited to, a promoter, an enhancer sequence, repressor sequence, TATA box, transcription stop sequence, ribosomal binding site, etc. One of skill in the art would appreciate the variety of elements that may be used in combination with the growth factor gene. These growth factor genes may also be transfected with an appropriate promoter, such as a cytomegalovirus promoter operably linked to the growth factor cDNA to be transcribed. In general, appropriate promoters should be selected for the cell type being transfected. In addition, the growth factors may be transfected with appropriate enhancer or repressor regions to further control expression of the growth factor gene being transfected. Effective enhancers and repressors for a variety of cells are well known to those skilled in the art. The genes may also be co-transfected with ribosomal binding sites or transcription stop and start sites to enhance the transcription of the growth factor gene. The DNA sequence may also include

flanking regions to facilitate incorporation of the genetic material into the chromosomes of the transfected cells.

Examples

Methods

5 Cells were transfected as described in Gene Therapy (Madry, 2000, the contents of which are incorporated herein by reference). Reagents were obtained from GIBCO Life Technologies (Grand Island, NY, USA) unless otherwise indicated. FUGENE 6™ (Boehringer Mannheim, Mannheim, Germany) is a non-liposomal mixture of lipids. Bovine testicular hyaluronidase was from Sigma (St. Louis, MO, 10 USA), Plasticware was from Falcon (Becton Dickinson Labware, Franklin Lakes, NJ, USA).

A human IGF-I cDNA (Jansen, *et al.* (1983) "Sequence of cDNA encoding human insulin-like growth factor I precursor." Nature 306: 609-11) from the plasmid pBShIGF-I containing the entire coding region was inserted as a 760 bp *Pst*I fragment 15 into pcDNA3.1/Zeo(+) (Invitrogen, Carlsbad, CA) containing the human cytomegalovirus immediate-early promoter/enhancer and the bovine growth hormone polyadenylation signal. The plasmid was designated pCMVhIGF-I. For the expression of β -galactosidase, the vector pCMVSPORT β Gal (Gibco Life Technologies, Grand Island, NY) containing the *E. coli lacZ* gene under the control of the CMV-IE 20 promoter/enhancer was used. Plasmids were subjected to endotoxin-free maxipreparation (Qiagen, Hilden, Germany).

Bovine articular cartilage was obtained from radiocarpal joints of 1 to 2-week old calves; the underlying vascularized cartilage was discarded. Harvested cartilage was washed, diced into 2 x 2 mm pieces and transferred to DMEM with 100 U/mL 25 penicillin G, 50 mg/mL ascorbic acid, and 100 μ L/ml streptomycin (basal medium)

containing collagenase at 37°C in a humidified atmosphere with 5% CO₂ for 16 h. Isolated cells were filtered through at 125 µm mesh to remove undigested matrix. Bovine chondrocytes were isolated with 0.08-0.09% collagenase. Cell number was determined by hemocytometry. Viability, as determined by trypan blue exclusion, always exceeded 90%. Isolated chondrocytes were placed in monolayer culture in 24-well plates at a density of 6 x 10⁴ cells per well in basal medium containing 10% fetal bovine serum (growth medium).

The cells were cultured for 3-4 days without passage until subconfluent (60-70% density) and divided into three groups. Group one served as a mock-transfected control. Group two was transfected with an *E. coli* β-galactosidase (*lacZ*) gene as a marker gene. Group three was the experimental group and was transfected with a human IGF-I expression vector pCMVhIGF-I using the FUGENE 6TM delivery system, as described below. For overexpression of human IGF-I (hIGF-I), the previously characterized expression plasmid vector pCMVhIGF-I that contains a hIGF-I cDNA (Jansen, 1983) under control of the human cytomegalovirus immediate-early promoter/enhancer (CMV-IE) and the bovine growth hormone polyadenylation signal was used (Madry, *et al.*, unpublished data).

The eukaryotic expression vector pCMVSPORTβGal containing the *E. coli lacZ* gene under the control of the cytomegalovirus immediately-early promoter and enhancer was propagated in DH5α competent cells. Ultrapure endotoxin-free plasmid DNA was prepared using the Quiagen Endofree Plasmid Maxi Kit according to the manufacturer's instructions. The chondrocyte monolayer was rinsed once with Opti-MEM. For transfections, non-liposomal lipid/DNA complexes were prepared according to the manufacturer's instructions in sterile polypropylene tubes and added to the chondrocytes. Cells were incubated at 37°C for 4 h, washed with DMEM and

incubated for a further 48 h with growth medium. The optimal (v/w) transfection (lipid)/DNA ratio is 3:1 for the bovine articular chondrocytes described above. The optimal quantity of DNA is 1 µg, and transfection efficiency is increased significantly by exposure to 4U/mL hyaluronidase both 12 hours before transfection and during
5 transfection (Madry, 2000). Similar transfection conditions also produce excellent results in human articular chondrocytes; however, a lipid-DNA ratio of 2:1 is preferred for osteoarthritic human chondrocytes.

Bovine articular chondrocytes transfected with pCMVhIGF-I secrete 83 ± 22 ng IGF-I per 1×10^7 cells/24h that is biologically active (Madry, *et al.*, unpublished
10 data). For the expression of β -galactosidase, the vector pCMVSPORT β Gal containing the *E. coli lacZ* gene under the control of the CMV-IE promoter/enhancer was applied. One day after transfection, cells were dissociated from the culture plates and dynamically seeded (5×10^6 cells/scaffold) in a nonwoven polyglycolic (PGA) mesh (Freed, *et al.* (1994) "Biodegradable polymer scaffolds for tissue engineering",
15 Biotechnology 12:689-693) (5 mm diameter x 2 mm thick disks) in basal medium supplemented with 10% calf serum. The mean cell viability after seeding was 95.2 ± 3.4 %, 94.8 ± 1.2 % and 94.9 ± 2.4 % for constructs based on pCMVSPORT β Gal-transfected, pCMVhIGF-I-transfected, or normal chondrocytes, respectively ($n = 3$, $P > 0.05$). After 2 days, constructs were transferred to rotating bioreactors (Synthecon,
20 Houston, TX) (Freed, *et al.* (1998) "Chondrogenesis in a cell-polymer-bioreactor system." Exp. Cell Res. 240: 58-65) and cultured freely suspended for up to 38 days post transfection. Constructs were sampled at day 10, 21, 28 and 38 post transfection.

Samples for gene expression were assayed for β -galactosidase activity by X-gal staining (Madry, 2000). Briefly, constructs were fixed for 10 min in 10 %
25 formalin and stained for 4 h at 37°C for β -galactosidase (*In-situ* β -galactosidase

Staining Kit, Stratagene). For histology and immunohistochemistry, constructs were fixed for 24 h in 10 % formalin. Paraffin-embedded sections (5 μ m) were stained with safranin O. For type-I and type-II collagen immunostaining, sections were deparaffinized in xylene, passed through decreasing concentrations of ethanol, washed in PBS and submerged for 30 min in 0.3 % hydrogen peroxide. After washing with PBS, sections were incubated for 30 min in 33 U/mL bovine testicular hyaluronidase (Sigma), washed with PBS and further incubated 30 min. in 10% horse serum in PBS (blocking buffer). Sections then were incubated with a 1:100 dilution of a monoclonal anti-bovine type-I collagen IgG (Sigma), a 1:20 dilution of an anti-bovine type-II collagen IgG (Developmental Studies Hybridoma Bank, Ames, IA, USA) or a 1:20 dilution of a monoclonal aggrecan (Serotec, Oxford, UK) in blocking buffer for 45 min. at room temperature. The primary antibody was detected by the Vectastain Elite ABC kit (Vector Laboratories, Burlingame, CA, USA) using diaminobenzidine as the chromogen. Positive controls included bovine articular cartilage with vascular structures (collagens type I and II, aggrecan) and rat skin (collagen type I). Negative controls included samples without the primary antibody, rat skin (type II and aggrecan) and bovine articular cartilage (type I collagen).

Morphometric measurements of the diameter of the cartilaginous constructs were performed standardized at the horizontal and vertical axis of a safranin-O stained horizontal section by image analysis using Adobe Photoshop 5.0 (Adobe Systems, Mountain View, CA).

Samples for biochemical analysis were lyophilized and digested for 16 h at 56°C with 1 mg/mL proteinase-K (Sigma) solution in 50 mM Tris, 1 mM EDTA, 1mM iodoacetamide with use of 1 mL of enzyme solution per 4 – 10 mg dry weight of the sample. The DNA content of the constructs was assessed by the Hoechst 33258

assay using a QM-1 spectrofluorometer (Photon Technology International, South Brunswick, NJ) (Kim, *et al.* (1988) "Fluorometric assay of DNA in cartilage explants using Hoechst 33258." Anal. Biochem. 174: 168-76). The glycosaminoglycan content of the constructs was determined spectrophotometrically (Perkin-Elmer, Norwalk, CT) with the use of dimethylmethylene blue (Serva, Darmstadt, Germany) (Farndale, *et al.* (1986) "Improved quantification of sulphated glycosaminoglycans by use of dimethylmethylene blue." Biochim. Biophys. Acta 883: 173-77). Total collagen content was determined from the measured hydroxyproline content after acid hydrolysis in 6N HCl at 115°C for 18 h and reaction with p-dimethylaminobenzaldehyde and choramine-T with the use of a hydroxyproline / collagen ratio of 1:10 (Woessner, *et al.* (1961) "The determination of hydroxyproline in tissue and protein samples containing small proportions of this imino acid." Arch. Biochem. Biophys. 93: 440-47). Collagen and proteoglycan synthesis rates were determined by measuring the incorporation of [³H] proline and [³⁵S] sulfate (NEN, Boston, MA), respectively as previously described (Freed, 1998).

To determine IGF-I protein production, engineered constructs (n = 2 per experiment) were individually incubated in 1 mL basal medium for 24 h at ten days post transfection. This conditioned medium or medium removed from the bioreactor was subjected to a three-step acid acid-ethanol extraction of binding proteins. The IGF-I content was determined by radioimmunoassay (detection limit: 20 ng/mL; Nichols Institute, San Juan Capistrano, CA) in 1 mL conditioned medium as described above or in the regular bioreactor culture medium in which the constructs were cultured.

For mechanical evaluation, engineered constructs were equilibrated for 1 h at room temperature in 0.15 M phosphate buffered saline (PBS, pH 7.4) supplemented

with 100 U/mL penicillin, 100 µg/mL streptomycin, and protease inhibitors, and cored into disks (3 mm diameter, 2 mm thickness). Samples were mounted in an electrically insulating cylindrical confining chamber as previously described (Frank, *et al.* (1987) "Cartilage electromechanics--II. A continuum model of cartilage electrokinetics and correlation with experiments." *J. Biomech.* 20: 629-39). The chamber was mounted in a servo-controlled Dynastat mechanical spectrometer (Imass, Hingham, MA), and the specimen was compressed between a porous polyethylene platen and an Ag/AgCl electrode, with an identical electrode placed in the surrounding bath. Pre-implantation samples were compressed at initial 10% strain and then sequential increments of 5% up to a maximum of 35%. Post-implantation samples were compressed at initial 5% strain and then sequential increments of 2% up to a maximum of 15%. After stress relaxation, the equilibrium stress was measured and plotted against the applied strain; the equilibrium modulus was determined from the slope of the best linear regression fit (Frank, 1987).

The protocol for *in vivo* implantation used was approved by the Animal Care and Use Committee at the Massachusetts Institute of Technology. Six constructs per group were sampled from bioreactors 28 days post transfection, implanted in dorsal subcutaneous pouches in immunocompromised mice (NIH Swiss Nude; 25-30 g, Charles River, Cambridge, MA), harvested after 10 more days and assayed for reporter gene expression, histological appearance and biomechanical properties.

Data are expressed as mean \pm SD. Four independent experiments were performed with 10 - 12 constructs per condition for bioreactor studies. Differences between groups were compared using two-way analysis of variance (ANOVA). A two-tailed $P < 0.05$ was considered statistically significant.

Results – Structural Properties

Constructs based on pCMVhIGF-I-transfected chondrocytes maintained their wet weight over the period of bioreactor cultivation, while the wet weights of constructs from non-transfected and pCMVSPORT β Gal-transfected chondrocytes decreased over time (Fig. 2). After 28 days of cultivation, the weight and the mean diameter of pCMVhIGF-I-transfected constructs were significantly higher than those of non-transfected or pCMVSPORT β Gal-transfected constructs (Tables 1 and 2).*

Table 1

Parameter	Genetically modified constructs		Normal constructs
	pCMVSPORT β Gal	pCMVhIGF-I	
Construct structure			
Weight (mg wet)	26.5 \pm 2.1 (n = 10, $P < 0.001$)	67.7 \pm 10.8 (n = 10)	29.0 \pm 8.5 (n = 10, $P < 0.001$)
Weight (mg dry)	2.2 \pm 0.4 (n = 10, $P < 0.001$)	5.8 \pm 1.1 (n = 10)	2.8 \pm 0.4 (n = 10, $P < 0.001$)
Diameter (mm)	5.6 \pm 0.1 (n = 10, $P < 0.001$)	6.5 \pm 0.2 (n = 10)	5.3 \pm 0.2 (n = 10, $P < 0.001$)
Water (%)	92.5 \pm 1.0 (n = 6, $P > 0.05$)	91.3 \pm 0.9 (n = 5)	88.7 \pm 3.5 (n = 6, $P > 0.05$)
DNA (ng per construct)	97.5 \pm 13.9 (n = 6, $P = 0.001$)	148.6 \pm 23.1 (n = 5)	76.8 \pm 14.0 (n = 6, $P = 0.001$)
GAG (μ g per construct)	96.3 \pm 15.3 (n = 6, $P = 0.001$)	1068.6 \pm 239.6 (n = 5)	133.3 \pm 51.1 (n = 6, $P < 0.001$)
GAG (μ g per ng DNA)	1.0 \pm 0.1 (n = 6, $P < 0.001$)	7.1 \pm 0.6 (n = 5)	1.7 \pm 0.4 (n = 6, $P < 0.001$)
Collagen (mg per construct)	0.6 \pm 0.1 (n = 6, $P < 0.001$)	1.3 \pm 0.2 (n = 2)	0.5 \pm 0.1 (n = 6, $P < 0.001$)
Collagen (g per ng DNA)	5.8 \pm 0.7 (n = 6, $P < 0.001$)	8.5 \pm 0.5 (n = 5)	7.1 \pm 1.0 (n = 6, $P = 0.015$)

Table 2

* Structural and functional parameters of engineered constructs based on pCMVSPORT β Gal-, pCMVhIGF-I-transfected or normal chondrocytes. All parameters were assessed at day 28 post transfection. Data represent mean \pm standard deviation. Statistical significance was assessed using ANOVA. Parentheses indicate the number of samples analyzed per group followed by the P value for comparing the respective control group with constructs based on pCMVhIGF-I-transfected chondrocytes.

Parameter	Genetically modified constructs		Normal constructs
	pCMVSPORT β Gal	pCMVhIGF-I	
Chondrocyte function			
Glucose in medium (mg / dl)	322.0 \pm 7.1 (n = 2, $P > 0.05$)	221.0 \pm 52.3 (n = 2)	311.5 \pm 20.5 (n = 2, $P > 0.05$)
Lactate in medium (mg / dl)	99.8 \pm 7.4 (n = 2, $P > 0.05$)	180.5 \pm 48.8 (n = 2)	103.5 \pm 12.0 (n = 2, $P > 0.05$)
[3 H] Proline incorporation (10^3 cpm / ng DNA / 16 h)	19.5 \pm 4.1 (n = 6, $P > 0.05$)	22.7 \pm 3.1 (n = 5)	21.8 \pm 3.6 (n = 6, $P > 0.05$)
[35 S] Sulfate incorporation (10^3 cpm / ng DNA / 16 h)	1.2 \pm 0.3 (n = 6, $P < 0.001$)	4.7 \pm 0.5 (n = 5)	1.9 \pm 0.5 (n = 6, $P < 0.001$)

At all time points, constructs incorporating pCMVhIGF-I-transfected chondrocytes appeared histologically more cartilaginous than those in the two control groups, as evidenced by the morphology of chondrocytes and the intensity of safranin O staining (Fig. 2C, 3A-C). After 28 days, immunohistological evaluation demonstrated the absence of type I collagen (Fig. 3D-F) and the presence of type II collagen (Fig. 3G-I) and aggrecan (Fig. 3K-M) in constructs in all groups. In constructs based on pCMVSPORT β Gal-transfected chondrocytes, X-gal-positive cells were found scattered throughout the construct until day 38 post-transfection, the endpoint of this study.

Constructs based on pCMVhIGF-I-transfected chondrocytes had a DNA content 1.5-fold higher than that of pCMVSPORT β Gal-transfected constructs and 1.9-fold higher than that of constructs based on normal chondrocytes (Table 1). The glycosaminoglycan content in constructs based on pCMVhIGF-I-transfected

chondrocytes was 11.1-fold higher than in constructs based on pCMVSPORT β Gal-transfected chondrocytes and 8-fold higher than in constructs based on normal chondrocytes. The total collagen content in constructs based on pCMVhIGF-I-transfected chondrocytes was 2.0-fold higher than in constructs based on pCMVSPORT β Gal-transfected chondrocytes and 2.4-fold higher than in constructs based on normal chondrocytes. The glycosaminoglycan content per ng DNA in constructs based on pCMVhIGF-I-transfected chondrocytes was 7.1-fold higher than in constructs based on pCMVSPORT β Gal-transfected chondrocytes and 4.2-fold higher than in constructs based on normal chondrocytes. The collagen content per ng DNA in constructs based on pCMVhIGF-I-transfected chondrocytes was 1.5-fold higher than in constructs based on pCMVSPORT β Gal-transfected chondrocytes and 1.2-fold higher than in constructs based on normal chondrocytes. Human IGF-I was not detected in the bioreactor culture medium or in conditioned medium from individually incubated engineered constructs.

15 Results – Functional Parameters

Macromolecular incorporation of [3 H] proline in constructs based on pCMVhIGF-I-transfected chondrocytes was not significantly different from constructs based on pCMVSPORT β Gal-transfected or normal chondrocytes (Table 1). The equilibrium modulus after 4 weeks in the pCMVhIGF-I-transfected group was 125.0 \pm 52.0, 4-fold higher than in the combined control groups (31.5 \pm 1.5, n = 4, P = 0.028).

Results - In vivo Gene Expression

Four-week constructs implanted subcutaneously in mice continued to develop into mature cartilaginous tissue. After 10 days *in vivo*, constructs were surrounded with a thin fibrous capsule. Constructs based on pCMVSPORT β Gal-transfected

- chondrocytes had equilibrium moduli of 35 +/- 33 kPa (n=3). The pCMVhIGF-I-transfected constructs had moduli of 126 +/- 52 kPa (n=4), and the non-transfected constructs had equilibrium moduli of 30 +/- 4 kPa (n=3). The pCMVhIGF-I-transfected constructs had significantly higher equilibrium moduli than either control.
- 5 Gene expression, as determined by X-gal staining of constructs based on pCMVSPORT β Gal-transfected chondrocytes persisted throughout the implantation period that ended on day 38 post transfection.

Discussion

- Transfer of a human IGF-I cDNA into primary articular chondrocytes
- 10 improved the structural and functional properties of bioengineered cartilaginous constructs. These results are consistent with previously reported data on the effects of IGF-I on isolated articular chondrocytes (Trippel, *et al.* (1989) "Effect of somatomedin-C/insulin-like growth factor I and growth hormone on cultured growth plate and articular chondrocytes." Pediatr. Res. 25: 76-82). Transgene expression was
- 15 maintained for up to 38 days post transfection *in vitro* and *in vivo*, and the resulting constructs were structurally cartilaginous and mechanically functional.

- The protocol for each transfection utilized a very short time in monolayer culture and no passaging of the chondrocytes, thereby avoiding phenotypic drift of the chondrocytes (von der Mark, *et al.* (1977) "Relationship between cell shape and type
- 20 of collagen synthesis as chondrocytes lose their cartilage phenotype in culture." Nature 267: 531-2). Both pCMVSPORT β Gal- and pCMVhIGF-I-transfected chondrocytes remained viable after dissociation from the cell culture vessel, indicating that neither the transfection procedure applied or nor the transgene products had adverse effect on chondrocyte viability.

- 25 Application of pCMVhIGF-I-transfected chondrocytes resulted in a faster rate

of chondrogenesis *in vitro*. In constructs incorporating pCMVhIGF-I-transfected chondrocytes, the amount of collagen, glycosaminoglycan and chondroitin sulfate per ng DNA was significantly higher than in constructs from the two control groups. This suggests that the higher amounts of these macromolecules, in particular collagen, per
5 construct are not secondary to an increase in cell number per construct, but rather reflect an augmented synthesis rate of these molecules by chondrocytes within the construct. These findings are consistent with the role of IGF-I in articular chondrocyte growth and matrix synthesis (Trippel, *et al.* (1995) "Growth factor actions on articular cartilage." *J. Rheumatol. Suppl.* 43: 129-32) and in articular cartilage repair (Nixon,
10 1999).

Constructs incorporating pCMVhIGF-I-transfected chondrocytes exhibited an increase in biosynthetic activity as measured by enhanced [³⁵S] sulfate incorporation, an index for glycosaminoglycan synthesis. Incorporation of [³H] proline, an index for collagen synthesis, remained unchanged between the groups. Their equilibrium
15 modulus, an intrinsic biomechanical parameter that reflects the ability to resist loading, was 4-fold higher as compared to the control constructs but remained subnormal after 10 days of *in vivo* cultivation. As previously shown, several months are necessary to obtain mechanical properties similar to that of native articular cartilage (Freed, 1997). Constructs from all groups continued to develop *in vivo*, were
20 mechanically functional following explantation, and maintained transgene expression.

The long availability of the plasmid DNA vector within component chondrocytes is likely to provide maximal benefit for the stimulation of chondrogenesis over a prolonged period of time. In a possible clinical application, the strong CMV-IE promoter/enhancer can be replaced with regulative elements that are
25 tissue-specific or responsive to physiological conditions (Kitamura, *et al.* (1997)

“Creation of an *in vivo* cytosensor using engineered mesangial cells. Automatic sensing of glomerular inflammation controls transgene activity.” J. Clin. Invest. **100**: 1394-9). Exemplary elements include a type II collagen or aggrecan promoter.

Of interest was the observation that the release of IGF-I from the cartilaginous construct into the culture medium could not be detected. In contrast, in previous experiments, we found significant levels of bioactive human IGF-I following transfection of bovine articular chondrocytes with FuGENE 6 (Madry, *et al.*, unpublished data). Recent data using adenoviral transduction of rabbit articular chondrocytes confirmed the capability of articular chondrocytes to synthesize and secrete bioactive human IGF-I (Smith 2000). It is possible that the IGF-I produced in the experimental constructs was bound to IGF-I binding proteins produced by chondrocytes within the cartilaginous construct (Olney, *et al.* (1993) “Production and hormonal regulation of insulin-like growth factor binding proteins in bovine chondrocytes.” Endocrinology **133**: 563-70). The effect of IGF-I appears to be limited to the cartilaginous construct by mechanisms that need to be further elucidated.

Tissue-engineered human bioartificial muscle composed of retroviral modified cells has been previously shown to express and to secrete pharmacologically relevant levels of recombinant human growth hormone (Vandeburgh, *et al.* (1996) “Tissue-engineered skeletal muscle organoids for reversible gene therapy.” Hum. Gene Ther. **7**: 2195-200; Powell, 1999). A sustained release of DNA *in vivo* was achieved when plasmid DNA was associated with a biodegradable carrier (Bonadio, 1999). Although the secretion of bioactive human IGF-I by keratinocytes (Eming, *et al.* (1996) “Targeted expression of insulin-like growth factor to human keratinocytes: modification of the autocrine control of keratinocyte proliferation.” J. Invest.

Dermatol. 107: 113-20), differentiated muscle fibers (Alila, *et al.* (1997) "Expression of biologically active human insulin-like growth factor-I following intramuscular injection of a formulated plasmid in rats." Hum. Gene Ther. 8: 1785-95; Barton-Davis, *et al.* (1998) "Viral mediated expression of insulin-like growth factor I blocks the aging-related loss of skeletal muscle function." Proc. Natl. Acad. Sci. U S A 95: 15603-7), or chondrocytes (Smith, 2000) has been reported, there have been no previous reports about the use of genetically modified cells for tissue engineering of cartilage.

In summary, this is the first time cells expressing an exogenous growth factor gene have utilized for the tissue engineering of cartilage. The application of gene delivery to the tissue engineering of cartilage resulted in enhanced structural and functional properties of engineered constructs. The characteristics of this system present an unique opportunity to evaluate the effect of different growth factors in a suitable model of chondrogenesis, *e.g.* by applying tissue – specific promoters such as the type II collagen or aggrecan promoters, using different cells as a source, or for applications different than articular cartilage repair.

Other embodiments of the invention will be apparent to those skilled in the art from a consideration of the specification or practice of the invention disclosed herein. It is intended that the specification and examples be considered as exemplary only, with the true scope and spirit of the invention being indicated by the following claims.

What is claimed is:

- 1 1. A method of assembling a tissue engineered construct, comprising:
2 transfecting a plurality of mammalian cells with a gene for a growth factor
3
- 4 2. The method of claim 1, further comprising culturing the cells until they
5 synthesize a desired amount of extracellular matrix.
6
- 7 3. The method of claim 1, further comprising seeding the cells onto a
8 biocompatible matrix.
9
- 10 4. The method of claim 3, wherein the matrix comprises a member of a synthetic
11 or a non-synthetic material.
12
- 13 5. The method of claim 4, wherein the matrix comprises a member of
14 poly(glycolic acid), collagen-glycosaminoglycan, collagen, poly(lactic acid),
15 poly(lactic-co-glycolic acid), poly(anhydride), poly(hydroxy acid),
16 poly(orthoester), poly(propylfumerate), polysaccharide, polypyrrole,
17 polyaniline, polythiophene, polystyrene, polyester, polyurethane, polyurea,
18 poly(ethylene vinyl acetate), polypropylene, polymethacrylate, polyethylene,
19 poly(ethylene oxide), poly(carbonate), and any combination thereof.
20
- 21 6. The method of claim 5, wherein the synthetic matrix comprises poly(glycolic
22 acid).
23
- 24 7. The method of claim 1, wherein the cells are human cells.
25

- 1 8. The method of claim 1, wherein the cells are selected from chondrocytes,
2 hepatocytes, Islet cells, nerve cells, muscle cells, bone forming cells,
3 fibroblasts, endothelial cells, stem cells, connective tissue stem cells,
4 mesodermal stem cells, and epithelial cells.
5
- 6 9. The method of claim 8, wherein the cells are chondrocytes.
7
- 8 10. The method of claim 1, further comprising adding a cell attachment facilitator
9 to the matrix, wherein the cell attachment facilitator comprises a member of
10 integrins, cell adhesion sequences, basement membrane components, agar, and
11 collagen.
12
- 13 11. The method of claim 1, further comprising adding a cell metabolism regulator
14 to the matrix.
15
- 16 12. The method of claim 1, wherein the growth factor is a protein.
17
- 18 13. The method of claim 12, wherein the growth factor is selected from TGF- β ,
19 TGF- α , acidic fibroblast growth factor, basic fibroblast growth factor,
20 epidermal growth factor, IGF-I and II, vascular endothelial-derived growth
21 factor, bone morphogenetic proteins, hepatocyte, platelet-derived growth
22 factor, heparin binding growth factor, hematopoietic growth factor, and peptide
23 growth factor.
24

- 1 14. The method of claim 13, wherein the growth factor is insulin-like growth
2 factor I.
3
- 4 15. The method of claim 1, wherein transfection is accomplished without a viral
5 vector.
6
- 7 16. The method of claim 15, wherein transfection comprises use of a lipid-based
8 delivery system.
9
- 10 17. The method of claim 1, wherein transfection is accomplished with a viral
11 vector.
12
- 13 18. A tissue engineered construct, comprising:
14 a mammalian cell transfected with a gene for a growth factor; and
15 a biocompatible synthetic matrix.
16
- 17 19. The tissue engineered construct of claim 18, wherein the cell is a chondrocyte.
18
- 19 20. The tissue engineered construct of claim 18, wherein the synthetic matrix
20 comprises poly(glycolic acid).
21
- 22 21. The tissue engineered construct of claim 18, wherein the growth factor is
23 insulin-like growth factor I.
24

- 1 22. A method of facilitating regeneration of cartilage, comprising:
2 transfecting a chondrocyte with a gene for a growth factor;
3 seeding the cell onto a biocompatible synthetic matrix;
4 implanting the cell-seeded matrix into an *in vivo* site.
5
- 6 23. The method of claim 22, wherein the synthetic matrix comprises poly(glycolic
7 acid).
8
- 9 24. The method of claim 22, wherein the growth factor is insulin-like growth
10 factor I.
11
- 12 25. The method of claim 22, wherein transfection is accomplished without a viral
13 vector.
14
- 15 26. The method of claim 25, wherein transfection comprises use of a lipid based
16 delivery system.
17
- 18 27. A transfection vector for a mammalian cell, comprising a gene for a growth
19 factor.
20

- 1 28. The transfection vectors of claim 27, wherein the cell is selected from
2 chondrocytes, hepatocytes, Islet cells, nerve cells, muscle cells, bone forming
3 cells, fibroblasts, endothelial cells, stem cells, connective tissue stem cells,
4 mesodermal stem cells, and epithelial cells.
5
- 6 29. The transfection vector of claim 27, wherein the growth factor is a protein.
7
- 8 30. The transfection vector of claim 29, wherein the growth factor is selected from
9 TGF- β , TGF- α , acidic fibroblast growth factor, basic fibroblast growth factor,
10 epidermal growth factor, IGF-I and II, vascular endothelial-derived growth
11 factor, bone morphogenetic proteins, hepatocyte, platelet-derived growth
12 factor, heparin binding growth factor, hematopoietic growth factor, and peptide
13 growth factor.
14
- 15 31. The transfection vector of claim 30, wherein the growth factor is insulin-like
16 growth factor I.
17
- 18 32. The transfection vector of claim 31, wherein the gene comprises human IGF-I
19 expression vector pCMVhIGF-I.
20
- 21 33. The transfection vector of claim 31, wherein the gene comprises an active
22 fragment that is 50% homologous to the complete gene for IGF-I.
23

- 1 34. The transfection vector of claim 33, wherein the gene comprises an active
2 fragment that is 75% homologous to the complete gene for IGF-I.
3
- 4 35. The transfection vector of claim 34, wherein the gene comprises an active
5 fragment that is 90% homologous to the complete gene for IGF-I.
6
- 7 36. The transfection vector of claim 31, wherein the transfected gene codes for a
8 portion of normal IGF-I that is 50% homologous to complete.
9
- 10 37. The transfection vector of claim 36, wherein the transfected gene codes for a
11 portion of normal IGF-I that is 75% homologous to complete IGF-I.
12
- 13 38. The transfection vector of claim 37, wherein the transfected gene codes for a
14 portion of normal IGF-I that is 90% homologous to complete IGF-I.
15
- 16 39. A plurality of transfected cells comprising chondrocytes, wherein the
17 chondrocytes are transfected with a gene for a protein.
18
- 19 40. A plurality of cells of claim 39, wherein the protein is a growth factor.
20
- 21 41. The plurality of cells of claim 40, wherein the growth factor is insulin like
22 growth factor I.
23

- 1 42. The plurality of cells of claim 41, wherein the cells are transfected with a
2 vector pCMVhIGF-I.
3

Fig. 1




Fig. 2





Figure 3



(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
26 September 2002 (26.09.2002)

PCT

(10) International Publication Number
WO 02/074912 A3

(51) International Patent Classification⁷: C12N 5/00,
15/85, 15/87, 15/09, 15/70, 15/74

(US). FREED, Lisa, E.; 34 Palfrey Road, Belmont, MA 02478 (US). LANGER, Robert; 98 Montvale Road, Newton, MA 02459 (US).

(21) International Application Number: PCT/US02/07805

(22) International Filing Date: 14 March 2002 (14.03.2002)

(74) Agent: JARRELL, Brenda, H.; Choate, Hall & Stewart, Exchange Place, 53 State Street, Boston, MA 02109 (US).

(25) Filing Language: English

(81) Designated States (*national*): CA, JP.

(26) Publication Language: English

(84) Designated States (*regional*): European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR).

(30) Priority Data:
09/809,456 15 March 2001 (15.03.2001) US

Published:

— with international search report

(71) Applicant: MASSACHUSETTS INSTITUTE OF TECHNOLOGY [US/US]; 77 Massachusetts Avenue, Cambridge, MA 02138 (US).

(88) Date of publication of the international search report:
3 April 2003

(72) Inventors: MADRY, Henning; Volhardstrasse 7, 66424 Homburg (DE). VUNJAK-NOVAKOVIC, Gordana; 305 Fitzmaurice Circle, Belmont, MA 02478 (US). TRIPPEL, Stephen, B.; 59 Woodland Road, Auburndale, MA 02114

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 02/074912 A3

(54) Title: TISSUE ENGINEERING ENHANCED BY THE TRANSFER OF A GROWTH FACTOR GENE

(57) Abstract: Tissue engineered constructs including a matrix and cells transfected with a gene for a growth factor. The constructs may be implanted into a tissue site, where the growth factor gene enhances a metabolic function furthering integration of the construct in the tissue site. If the matrix is biodegradable, the metabolic result may include resorption of the matrix and replacement with tissue synthesized at least in part by the transfected cells.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US02/07805

A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : C12N 5/00, 15/85, 15/87, 15/09, 15/70, 15/74

US CL : 435/325, 383, 395, 455, 320.1, 401

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 435/325, 383, 395, 455, 320.1, 401

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
Please See Continuation Sheet

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5,785,964 A (NAUGHTON et al.) 28 July 1998 (28.07.1998), see entire document.	1-42
A	US 5,962,325 A (NAUGHTON et al.) 05 October 1999 (05.10.1999), see entire document.	1-42
A	US 6,083,523 A (DIONNE et al.) 04 July 2000 (04.07.2000), see entire document.	1-42
A	US 6,110,737 A (ESCOBEDO et al.) 29 August 2000 (29.08.2000), see entire document.	1-42

☐ Further documents are listed in the continuation of Box C.

☐ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"B" earlier application or patent published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

18 November 2002 (18.11.2002)

Date of mailing of the international search report

14 JAN 2003

Name and mailing address of the ISA/US

Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703)305-3230

Authorized officer

Felicia D. Roberts
(Konstantina Katcheves)

Telephone No. (703) 308-1235

Form PCT/ISA/210 (second sheet) (July 1998)

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US02/07805

Continuation of B. FIELDS SEARCHED Item 3:

STN, CAPLUS, MEDLINE, BIOSIS, EAST

search terms: tranfect, transform, cell; growth factor, IGF, TGF, culture, matrix, scaffold

Form PCT/ISA/210 (second sheet) (July 1998)

THIS PAGE BLANK (USPTO)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☒ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)